

Technical Data Sheet BR 5181-085

Physical Properties		
Grammage / Basis weight / Gewicht	85	g/m ²
Epaisseur / Thickness / Dicke	204	µm
Perméabilité 196 Pa / Permeability 196 Pa / Luftdurchl. 196 Pa	705	L/m ² /s
Rupture Sens Machine / Tensile Strength MD / Bruchlast Längss	3060	N/m
Rupture Sens Travers / Tensile Strength CD / Bruchlast Quer	2240	N/m
Allongement Sens Machine / Elongation MD / Dehnung Längs	26	%
Allongement Sens Travers / Elongation CD / Dehnung Quer	33	%
Déchirure Trapèze SM / Trapezium Tear MD / Weiterreissfest. L	2130	cN
Déchirure Trapèze ST / Trapezium Tear CD / Weiterreissfest. Q	2660	cN
Rapport Humide/Sec Ratio Wet/Dry Verhältnis Nass/Trocken	73	%
Goutte d'eau / Water Drop Test / Tropfentest Wasser	> 999	s

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as Ahlstrom deems appropriate. Refer to www.ahlstrom.com for contact information.

©2006-2011 Ahlstrom Corporation

Ahlstrom - Brignoud
revised novembre 14, 2006

